

COMPREHENSIVE HEMP PAPER MANUFACTURING SOP

Complete Replacement for Industrial Wood-Pulp Paper Products

Province: New Brunswick, Canada

Regulatory Framework: Industrial Hemp Regulations (SOR/98-156), Pulp and Paper Effluent Regulations (SOR/92-269), Canadian Environmental Protection Act

Vision: Sustainable replacement for all paper products currently manufactured from clear-cut forestry

Status: Finalized Production Standards

Version: 1.0

EXECUTIVE SUMMARY: THE HEMP ALTERNATIVE

The Forest Crisis

Industrial paper manufacturing in Atlantic Canada (particularly Irving operations) relies on **clear-cutting old-growth forests**, converting diverse ecosystems into monoculture softwood plantations. A 40-year rotation cycle means:

- Irreversible carbon release during harvest and transport.
- Habitat destruction (songbird breeding grounds, old-growth species loss).
- Water table disruption and erosion in clear-cut zones.
- Regional economic lock-in to resource extraction rather than sustainable agriculture.

The Hemp Solution

Hemp produces equivalent paper products using a 4-month agricultural crop cycle:

- Annual renewable rotation (harvest every 120 days).
- No clear-cutting; crop integrates into existing agricultural infrastructure.

- Lower chemical input (soda-AQ vs. Kraft pulping reduces environmental toxicity).
 - 25–30 tonnes dry matter per hectare annually (equivalent to 4–5 times faster biomass than commercial pine).
 - **Net result:** Replace 10 years of Irving clear-cut forestry with 4 years of hemp agriculture on equal acreage.
-

PART 1: COMPREHENSIVE PRODUCT PORTFOLIO

This SOP covers **all paper products currently manufactured by Irving Consumer Products** and equivalent industrial tissue/offset manufacturers, now produced from organic hemp:

A. TISSUE PRODUCTS (Bathroom Tissue, Facial Tissue, Napkins)

A1. Bathroom Tissue (Toilet Paper)

Specifications:

- **Weight:** 20–27 gsm (2-ply), 30–40 gsm (3-ply).
- **Brightness:** 80–90 ISO (achieved via ECF hydrogen peroxide bleaching).
- **Softness:** Caliper 0.15–0.25 mm per ply; creping for softness development.
- **Wet Strength:** 100–150 g/15 mm (wet-tensile per TAPPI T-231) via plant-derived starch binders.
- **Absorbency:** 5–8 g water per 1 g paper (critical for performance).
- **Production:** Tissue creping machine (Yankee dryer + doctor blade) for texture development.
- **Roll sizes:** Jumbo parent rolls (1,500 mm width) → converted to commercial retail (4.5", 10 cm widths) on downstream slitting equipment.

Volume Replacement Target:

- Irving annual tissue output: ~300,000–400,000 tonnes globally; North American share ~150,000 tonnes.
- Hemp toilet paper production target: 50,000–80,000 tonnes/year (Year 5) = direct replacement for 1/3–1/2 of North American tissue demand currently met by Irving.

A2. Facial Tissue (Scotties/Kleenex Alternative)

Specifications:

- **Weight:** 17–22 gsm (single-ply or 2-ply).
- **Brightness:** 85–92 ISO (premium white aesthetic).
- **Softness & Fluffiness:** High creping (40–60% creping ratio) for cushioning.
- **Strength:** Tensile 8–12 N per cm width (sufficient for nose-blowing use).
- **Wet Strength:** 20–40 g/15 mm (lower than toilet paper; allows tissue dissolution).
- **Lotion Compatibility:** If lotion-treated, use plant-derived oils (coconut, jojoba) instead of petrochemical formulations.
- **Production:** Creping machine optimized for high-loft tissue; optional embossing for premium aesthetics.

Volume Replacement Target:

- Irving (Royale) facial tissue annual volume: ~40,000 tonnes North America.
- Hemp facial tissue target: 15,000–25,000 tonnes/year (Year 5).

A3. Paper Napkins (Table Napkins, Lunch Napkins)

Specifications:

- **Weight:** 17–22 gsm (single-ply), 30–40 gsm (multi-ply, premium).
- **Brightness:** 80–85 ISO (natural cream acceptable for premium positioning).
- **Size:** 13" × 13" folded (standard lunch napkin); 7" × 7" cocktail size.
- **Strength:** Multi-directional tear strength (no preferred direction); ~8–12 N/cm tensile.
- **Absorbency:** High (napkin primary function).
- **Production:** Napkin folding machine (automated fold and pack).
- **Decorative Options:** Pre-printed designs, embossing, custom branding.

Volume Replacement Target:

- Irving napkin production: ~20,000 tonnes/year.
- Hemp napkin target: 8,000–12,000 tonnes/year (Year 5).

B. OFFSET & PRINTING PAPERS

B1. Premium Unbleached/Natural Offset (70–100 gsm)

Specifications:

- **Brightness:** 75–82 ISO (warm, natural aesthetic; not pure white).
- **Basis Weight:** 70 gsm (body text), 80 gsm (standard), 100 gsm (art books, premium).
- **Gloss/Finish:** Uncoated matte (natural hemp fiber texture).
- **Opacity:** $\geq 85\%$ (single-pass printing without show-through).
- **Smoothness:** 200–400 mL Bendtsen (rougher than commodity, aesthetically valued).
- **Brightness Consistency:** CIE L* 85–88 (achieved via ECF bleaching without additional coating).
- **Acid-Free/Archival:** pH 7.0–8.5 (100+ year permanence).

Applications:

- Book printing (trade publishing, limited editions, art books).
- Corporate printing (annual reports, brochures, marketing collateral).
- Magazine printing (literary journals, trade publications).
- Packaging (kraft-grade unbleached for wrapping, box board).

Volume Replacement Target:

- Industrial offset paper market (North America): ~2.5M tonnes/year.
- Hemp unbleached offset target: 200,000–400,000 tonnes/year (Year 5–10) = direct replacement for 8–16% of offset market.

B2. Bleached Bright Offset (70–90 gsm)

Specifications:

- **Brightness:** 85–89 ISO (achieved via ECF hydrogen peroxide bleaching).
- **Basis Weight:** 70 gsm (standard), 80–90 gsm (premium).

- **Coating:** Uncoated (matte) or lightly coated for enhanced smoothness.
- **Opacity:** $\geq 88\%$ (single-pass printing).
- **Surface Finish:** Smooth (via machine calendering), CIE L* 88–90.
- **Archival:** Acid-free, 100+ year durability.

Applications:

- General commercial printing (letterheads, business cards, promotional materials).
- Offset newspaper (if higher quality than commodity newsprint).
- Direct mail (brochures, catalogs).
- Educational materials (textbooks, workbooks).

Volume Replacement Target:

- Bleached offset market: ~1.8M tonnes/year (North America).
- Hemp bleached offset target: 150,000–300,000 tonnes/year (Year 5–10).

B3. Newsprint (45–52 gsm, High-Speed Offset)

Specifications:

- **Brightness:** 60–65 ISO (natural; newsprint traditionally not bright white).
- **Basis Weight:** 45–52 gsm (standard newsprint).
- **Opacity:** $\geq 85\%$ (prevent show-through on thin basis weights).
- **Porosity:** 20–40 seconds Gurley (rapid ink absorption for high-speed presses).
- **Runnability:** High wet-strength to prevent web breaks on newspaper presses (800+ m/min).
- **Cost:** Target price competitive with wood-pulp newsprint (\$700–900/tonne).

Applications:

- Newspaper printing (community newspapers, regional dailies).
- Coupon/flyer printing (high-volume distribution).
- Insert printing (retail/commercial).

Volume Replacement Target:

- North American newsprint market: ~3M tonnes/year.
 - Hemp newsprint target: 300,000–500,000 tonnes/year (Year 5–10) = price-competitive direct replacement.
-

C. PACKAGING & SPECIALTY GRADES

C1. Kraft Pulp Packaging (Unbleached/Natural)

Specifications:

- **Strength Grade:** Test Liner (TL-350–500, suitable for single/double-wall corrugating flute).
- **Brightness:** 50–65 ISO (natural kraft aesthetic).
- **Tensile Strength:** 20–35 N/m machine direction (meets corrugated board standards).
- **Tear Resistance (Elmendorf):** 60–100 mN (EN 1974 standard).
- **Moisture Tolerance:** Retains performance at 40–70% RH (critical for shipping boxes).
- **Basis Weight:** 80–150 gsm (box liners, fluting substrate).
- **Compostability:** Industrial biodegradable per EN 13432 (edge case; most kraft packaging not yet certified).

Applications:

- Corrugated board (shipping boxes, cardboard packaging).
- Paper bags (grocery, food service, retail).
- Wrapping paper (kraft wrapping, butcher paper).
- Protective packaging (tissue wrap, cushioning).

Volume Replacement Target:

- Kraft packaging market (North America): ~8M tonnes/year (Irving supplies ~15–20% via private label LDC).
- Hemp kraft packaging target: 400,000–800,000 tonnes/year (Year 5–10) = scalable replacement for commodity packaging.

C2. Bleached Packaging & Specialty Kraft

Specifications:

- **Brightness:** 75–82 ISO (bleached kraft for food-contact and premium packaging).
- **Food-Safety:** FDA CFR 176.170 compliance (if direct food contact required).
- **Grease Resistance:** 10–12 hours (if coated with PE or bio-wax; optional).
- **Tear Strength:** 80–120 mN (Elmendorf).
- **Tensile:** 25–40 N/m (suitable for premium bags, food service).
- **Compostability:** Certified EN 13432 (if PE-free or bio-coated with PLA).

Applications:

- Premium shopping bags (retail, luxury goods).
- Food service bags (bakery, butcher, deli packaging).
- Specialty envelopes (windowed, self-sealing).
- Food wrapping (if PE-free or compostable-coated).

Volume Replacement Target:

- Bleached specialty kraft: ~1.2M tonnes/year (North America).
- Hemp bleached specialty kraft target: 80,000–200,000 tonnes/year (Year 5–10).

C3. Coated & Specialty Grades

Specifications:

- **Coating:** Optional PE (polyethylene), PLA (polylactic acid, compostable), or wax-based (compostable).
- **Brightness:** 85–90 ISO (coated for glossy appearance).
- **Coating Weight:** 20–40 gsm per side (double-sided or single-sided options).
- **Barrier Properties:** Grease/water resistance (PE or wax coating achieves 1–4 hours).
- **Print Performance:** Excellent ink acceptance; gloss 20–40% (45° geometry).
- **Recyclability:** PE-coated stock recyclable in mixed-paper streams; PLA/wax versions compostable.

Applications:

- Coated box board (premium product packaging, luxury goods).
- Laminated specialty papers (labels, stickers with backing).
- Waterproof wrapping (meat, deli, food service).
- High-gloss printing (color catalogs, art printing, brochures).

Volume Replacement Target:

- Coated specialty market: ~600,000 tonnes/year (North America).
 - Hemp coated specialty target: 50,000–150,000 tonnes/year (Year 5–10).
-

D. SPECIALTY & NICHE PRODUCTS**D1. Tissue-Grade Specialty (Napkin, Towel, Medical Grades)****Applications:**

- Paper towels (kitchen roll, commercial dispenser rolls) — 25–35 gsm, high absorbency.
- Medical/surgical paper (exam table liners, bibs) — 28–40 gsm, wet-strength optimized.
- Industrial wipes (cleanroom, lab use) — 30–50 gsm, linting minimized.

Production: Multi-ply creping (2–3 layers) for towel grades; wet-strength optimization via starch/chitosan.

Volume: 15,000–25,000 tonnes/year (North America replacement target).

D2. Filter & Technical Papers**Specifications:**

- **Basis Weight:** 50–150 gsm (depends on application).
- **Porosity:** Highly variable (coffee filter: 30–60 sec Gurley; air filter: 5–20 sec Gurley).
- **Wet Strength:** Critical for water-immersed applications.
- **Particle Retention:** Consistent fines level to achieve target ISO 4572 ratings (16

micron, 25 micron, etc.).

Applications:

- Coffee filters (food-grade, compostable).
- Air filters (automotive, HVAC, industrial).
- Oil/liquid filters.
- Laboratory filtration.

Volume: 5,000–10,000 tonnes/year (specialized applications, smaller market but high margin).

PART 2: INTEGRATED HEMP PRODUCTION SYSTEM

Section 1: Agricultural Foundation (Upstream)

1.1 Cultivar & Yield Optimization

Hemp Cultivars by Product Application:

Cultivar	Bast Fiber %	Hurd %	Best Application
Finola (monoecious)	24–27%	73–76%	Tissue, newsprint (mixed fiber blend)
Bialobrzeskie (dioecious)	28–32%	68–72%	Premium offset, packaging (high-quality fiber)
CFX-2 (monoecious)	22–25%	75–78%	Tissue, commodity newsprint
NWG 2463 (dioecious)	26–30%	70–74%	Packaging, kraft grades

Target Yield per Hectare:

- Dry straw yield: 8–12 tonnes/hectare/year (4-month cycle = 3 rotations/year potential in southern NB climate).
- Bast fiber recovery: 2.0–3.2 tonnes/hectare/year (24–27% bast × 8–12 tonne straw).

- Hurd recovery: 5.7–8.6 tonnes/hectare/year (residual woody material for biofuel or composite applications).

Acreage Requirements (for full portfolio production):

- Target total paper production: 500,000–1M tonnes/year (Year 5–10, all product categories).
- At 10 tonnes straw/hectare, average fiber recovery ~60% effective yield = 6 tonnes usable fiber/hectare.
- Required acreage: 83,000–167,000 hectares (Saint John River Valley + Kennebecasis Valley, NB).
- **Context:** Irving's timber holdings in NB: ~1.8M hectares. Hemp acreage requirement = 5–9% of Irving's landbase (fully feasible geographic replacement).

1.2 Soil & Land Preparation

- **Rotation:** Hemp integrates into existing agricultural rotations; typically 2-year break from previous crop.
- **Soil Amendment:** Post-harvest hemp straw returns ~40% biomass carbon to soil (improves soil organic matter).
- **Drainage:** Hemp requires well-drained loamy soils (pH 6.0–7.5); tolerates marginal agricultural land (Irving clearcuts can regenerate as productive hemp cultivation zones within 1–2 seasons).

1.3 Seeding & Cultivation

Seeding Rate: 45–60 kg/ha (high-density monoecious), 25–40 kg/ha (dioecious fiber types).

Harvest Window: 70–90 days post-seeding (early flowering for optimal fiber quality).

Field Retting: 14–21 days (natural moisture separation of bast from woody core).

Yield Optimization:

- High-density (45–60 kg/ha) favors bast fiber development (25–30% bast yield).
 - Lower density (20–30 kg/ha) favors hurd size/quality but reduces total fiber per hectare.
 - **Production strategy:** For tissue/offset (mixed fiber use), high-density is optimal. For premium packaging (bast-optimized), lower density acceptable.
-

Section 2: Decortication & Fiber Preparation

2.1 Bale Conditioning

- **Moisture Content:** Condition to $\leq 12\%$ via rotary drum dryer (prevents fiber jamming).
- **Throughput:** 500–800 kg/hour per decorticator unit (scale multiple units for industrial volume).

2.2 Industrial Decorticator (Multi-Stage)

Equipment:

- Primary hammer mill: Shatters woody core into hurds (≤ 5 mm).
- Secondary pin mill: Further reduces hurd particle size; strips long bast fibers.
- Adjustable gap clearance: 8–12 mm (controls hurd fragmentation).

Output:

- Bast fiber fraction: 85–92% purity (remainder: short hurd contamination).
- Hurd fraction: $\leq 3\%$ bast contamination (remainder: usable woody fiber).

2.3 Pneumatic Separation & Cleaning

- **Air Classification:** High-velocity cyclones (≥ 20 m/s) separate light bast from heavy hurds.
 - **Fines Removal:** Secondary air classification removes dust, silica, non-fibrous material.
 - **Target Purity:** $\geq 95\%$ bast in primary fraction; $\leq 3\%$ bast in hurd fraction.
-

Section 3: Chemical Pulping (Soda-AQ Process)

3.1 Digester Configuration & Parameters

Reactor Type: Continuous vertical pressure vessel (5,000–10,000 L capacity for industrial scale).

Cooking Profile:

- **Ramp to 160 °C:** 90 minutes controlled heating.
- **Hold at 160 °C:** 45–60 minutes (H-factor: 1,000–1,100).
- **Operating Pressure:** 0.8 MPa (8 bar gauge) at 160 °C.
- **Alkali Charge:** 15% active alkali (NaOH equivalents), derived from renewable hydroelectric caustic soda.
- **AQ Catalyst:** 0.1% w/w (accelerates delignification, improves yield).
- **Liquor-to-Solids:** 4:1 (adequate chemical penetration).

Expected Yields by Fiber Fraction:

Feedstock	Screened Yield %	Kappa Number	Viscosity (cm ³ /g)	Target Application
Bast fibers (primary)	50–55%	12–16	750–850	Tissue, printing papers (high quality)
Hurd (woody core)	35–42%	18–24	500–650	Newsprint, commodity offset, packaging
Mixed fiber (30% bast)	42–48%	14–18	650–750	Tissue (mixed-fiber blends)

Optimization Strategy:

- **Tissue applications:** Blend 60% bast + 40% hurd for cost-efficiency (acceptable tissue quality).
- **Premium offset:** Use 80–100% bast fiber (superior strength, brightness).
- **Newsprint/packaging:** Use 100% hurd fraction (economical, sufficient strength for commodity).

3.2 Black Liquor Recovery & Chemical Regeneration

Multi-Stage Brown Stock Washing:

- Countercurrent washing with recovered white liquor (spent cooking solution).
- 5-stage cascade removes residual cooking chemicals, enabling 85–92% chemical recovery.

Lignin Valorization:

- **Agricultural Amendment:** Recover technical lignin as soil conditioner for hemp cultivation fields (closed-loop nutrient cycling).
- **Biofuel:** Dry black liquor solids (70–80% calorific value) co-fired in recovery boiler to offset external steam demand.
- **Byproducts:** Capture tall oil (if using soap recovery); valorize as industrial lubricant/binder.

Caustic Soda Regeneration (Lime Cycle):

- Recovery boiler: Burn black liquor solids (Na_2CO_3 , Na_2S , lignin) at high temperature.
- Lime kiln: Regenerate caustic soda from $\text{Na}_2\text{CO}_3 + \text{CaO} \rightarrow \text{NaOH}$ via standard kraft mill chemistry.
- **Chemical Recovery Rate:** 85–92% (minimizes external chemical purchases).

Zero-Liquid-Discharge Target:

- All spent pulping liquor recovered for caustic regeneration.
- Minimal wastewater discharge; 100% of cooking chemicals recirculated within mill.

Section 4: Pulp Refining & Stock Preparation

4.1 Fiber Beating & Freeness Development

Equipment: Twin-disc refiners or conical Hollander beaters.

Freeness Targets by Product:

Product Class	Canadian Standard Freeness (CSF)	Rationale
Tissue (toilet paper)	450–550 mL	High freeness = rapid drainage in creping machine; soft feel
Facial tissue	480–580 mL	Very high freeness for fast machine speeds; loft development
Napkins	350–450 mL	Moderate refining for balanced strength/absorbency
Offset		

(book/magazine)	300–400 mL	Lower freeness = better runnability on offset presses; enhanced printability
Newsprint	350–450 mL	Balanced freeness for high-speed newspaper production
Kraft packaging	400–500 mL	Higher freeness for rapid drainage; cost efficiency

Refining Energy: 300–500 kWh/tonne (varies by target freeness and fiber type).

4.2 Additives & Sizing

Wet-Strength Agents (Replace Synthetic PAE):

- Plant-derived starch (corn, potato, tapioca): 5–8 kg/tonne.
- Chitosan (bio-based, from crustacean shells): 2–3 kg/tonne.
- Glyoxalated polyacrylamide (GPA): 1–2 kg/tonne (if mineral-free not required).

Sizing System (Neutral-to-Alkaline pH 7.5–8.0):

- Alkyl Ketene Dimer (AKD): 8–12 kg/tonne (water resistance).
- Precipitated Calcium Carbonate (PCC): 15–20% loading (brightness, opacity without chlorine bleaching).

Retention Aids:

- Cationic polyacrylamide (CPAM): 1–2 kg/tonne (improve filler/fiber retention on forming wire).

Optional Lotion/Scent (Tissue only):

- Plant-derived aloe vera extract or jojoba oil (premium tissue grades).
- Natural fragrance (eucalyptus, lavender essential oils) instead of synthetic fragrances.

Section 5: Paper Machine Operations (Fourdrinier & Creping Systems)

5.1 Fourdrinier Wire Section (General Offset, Packaging, Newsprint)

Machine Specifications:

- **Wire Speed:** 300–600 m/min (depends on paper grade and basis weight).
- **Forming Wire:** Stainless steel, 200–250 mesh.
- **Vacuum Suction:** 40–65 kPa gauge (accelerates water drainage).
- **Sheet Uniformity:** Coefficient of variation <2.5% (weight distribution control).

Consistency & Headbox:

- **Target Consistency:** 0.3% solids (pulp suspension).
- **White Water Recirculation:** 50–70% recovery (reduces fresh water demand).

Press Sectioning:

- **Granite/Polyurethane Nip Rolls:** 500–800 kN/m pressure.
- **Moisture Reduction:** 80% (wet web) → 45% (press output).
- **Multiple Nip Stations:** 3–4 successive presses for gradual dewatering.

5.2 Tissue Creping Machine (Tissue, Facial Tissue, Towels)

Yankee Dryer Setup:

- **Yankee Cylinder:** 3.5–4.5 m diameter, steam-heated to 160–200 °C.
- **Drying:** Single-pass drying to ~95% solids (tissue must be crispy for creping).
- **Doctor Blade:** Precision ceramic blade (0.1–0.3 mm gap) scrapes tissue off Yankee.

Creping Variables (Tissue Softness):

- **Creping Ratio:** 20–40% (higher = softer, more loft; lower = stronger, denser).
- **Blade Pressure:** 100–300 N/m (higher pressure = tighter creping).
- **Yankee Temperature:** 160–180 °C (higher = faster drying, tighter creping).
- **Speed:** 400–800 m/min (typical tissue line speed).

Output:

- **Texture & Softness:** Creping creates wavy, elastic texture (characteristic tissue feel).
- **Absorb Capacity:** 5–8 g water/g tissue (critical for functional performance).

5.3 Multi-Cylinder Drying (All Products)

Dryer Stack:

- Steam-heated cast-iron cylinders (1.2–1.5 m diameter).
- **Temperature Progression:**
 - Zone 1 (Cylinders 1–2): 80 °C (remove surface moisture).
 - Zone 2 (Cylinders 3–4): 95 °C (bulk drying).
 - Zone 3 (Cylinders 5–6): 110 °C (final drying).
 - Zone 4 (Draw): 115 °C (equilibration).
- **Residence Time:** 5–8 seconds per cylinder group (~45–60 seconds total).

Target Moisture: 5–7% (equilibrium with 50% ambient RH).

5.4 Calendering & Finishing

Machine Calender:

- 3–5 polished steel rolls; adjustable pressure (100–300 kN/m).
- **Functions:** Control thickness ($\pm 5\%$ uniformity), eliminate surface fuzz, achieve target porosity.

Surface Properties (by Product):

Product	Gurley Porosity (sec)	Bendtsen Smoothness (mL/min)	Gloss (45° %)
Tissue	100–200 (high porosity)	— (not applicable)	— (natural matte)
Offset (Uncoated)	60–120	200–400	10–20%
Offset (Lightly Coated)	20–40	100–150	30–45%
Newsprint	80–150	250–500	5–10%
Kraft Packaging	40–100	300–600	— (natural kraft)

5.5 Winding, Slitting & Packaging

Winding:

- Parent reels up to 3,500 mm width; reel diameter up to 1,500 mm.
- Wind speed: 400–600 m/min (synchronized with dryer output).

Slitting:

- Precision knife or razor-blade slitter converts parent reels to master rolls or cut-size sheets.
- Standard sizes: A4 (210 × 297 mm), A3 (297 × 420 mm), B5 (176 × 250 mm), letter (8.5" × 11"), legal (8.5" × 14").
- Tissue rolls: 4.5" width (standard retail), 10 cm (metric markets), 2.5" (compact travel size).

Final Packaging:

- Moisture-barrier wrap (kraft or polyethylene film) maintains ≤7% moisture during storage.
- Shelf life: 12 months at 50% RH.
- **Tissue Special Handling:** Wrapped in plastic or cardboard sleeves to maintain softness and loft during distribution.

Section 6: Quality Assurance & Testing

6.1 Pulp Quality Standards

Testing Protocol (TAPPI Standards):

Parameter	Standard	Target Range	Rationale
Screened Yield	TAPPI T-257	48–54%	Pulping efficiency; economic metric
Kappa Number	TAPPI T-236	12–18 (avg 14)	Residual lignin; bleachability predictor
Viscosity	TAPPI T-230	≥700 cm³/g	Fiber length preservation
ISO Brightness	ISO	60–88% (depends	Unbleached ~65%; ECF

	2470-1	on product)	bleached ~85–88%
Permanent Wet Strength	TAPPI T-231	Varies by product	Tissue: 100–150 g/15mm; offset: minimal

6.2 Paper Product Standards

Tissue Papers (TAPPI/ANSI Standards):

Product	Basis Weight (gsm)	Tensile Strength	Tear Strength (Elmendorf, mN)	Brightness (ISO %)
Toilet Paper	20–27	3–8 N/m	60–100	80–90
Facial Tissue	17–22	4–8 N/m	40–80	85–92
Napkins (Multi-ply)	30–40	8–15 N/m	80–120	80–85
Paper Towels	30–40	15–25 N/m	100–150	75–85

Printing Papers (ISO Standards):

Product	Basis Weight (gsm)	Brightness	Opacity %	Tensile (N/m MD)	Tear (mN MD)
Offset (Unbleached)	70–100	75–82 ISO	≥85	35–50	80–120
Offset (Bleached)	70–90	85–89 ISO	≥88	38–55	85–130
Newsprint	45–52	60–65 ISO	≥85	25–40	60–100
Magazine/Coated	70–150	85–90 ISO	≥88	40–60	90–140

Packaging Papers (ISO/TAPPI Standards):

--	--	--	--	--	--

Product	Basis Weight (gsm)	Brightness	Burst Strength (kPa)	Tear (mN MD)	Tensile (N/m MD)
Kraft Packaging	80–150	50–65 ISO	3.0–5.0	80–150	25–45
Bleached Kraft (Food)	80–120	75–82 ISO	2.5–4.5	70–120	22–40
Kraft Board (Corrugating)	100–200	55–70 ISO	4.0–6.0	100–180	30–55

6.3 Regulatory & Environmental Compliance

Effluent Standards (Pulp & Paper Effluent Regulations, SOR/92-269):

- **BOD₅ (Biochemical Oxygen Demand):** <25 mg/L (discharged).
- **TSS (Total Suspended Solids):** <20 mg/L (discharged).
- **Acute Fish Toxicity:** No lethality at 100% mill effluent (OECD 203, 96-hour test).

Bleaching Sequence (ECF – Elemental Chlorine-Free):

- **Stage 1 (H₂O₂):** 10–15 kg/tonne H₂O₂; pH 9.5–10.0; 60 °C; 2–3 hours.
- **Mild Acid Wash:** pH 4.0–4.5 (remove metal complexes).
- **Stage 2 (Optional O₂):** 90 °C, 8 bar oxygen (if targeting ≥88 ISO brightness with minimal peroxide).

Target Brightness:

- Unbleached pulp: 60–65 ISO.
- Bleached pulp: 85–88 ISO (ECF sequence).

Certifications to Maintain:

- **FSC Certification:** Forest Stewardship Council (if applicable; may be waived for hemp, as no forest clearcut involved).
- **Organic Hemp Certification:** USDA Organic for cultivation; carries through to finished product claims.
- **Industrial Composability:** EN 13432 certification (if compostable packaging desired; requires PE-free or PLA coating).

PART 3: PRODUCTION VOLUMES & MARKET REPLACEMENT

Section 1: Full Product Portfolio Capacity (Year 5–10)

Target Annual Production Mix

Product Category	Annual Volume (tonnes)	% of Total Capacity	ASP (CAD/tonne)	Annual Revenue
Tissue Products	100,000–150,000	15–20%	\$950–1,200	\$95M–\$180M
— Toilet paper	50,000–75,000	—	\$1,100–1,300	\$55M–\$97.5M
— Facial tissue	30,000–40,000	—	\$900–1,100	\$27M–\$44M
— Napkins & Towels	20,000–35,000	—	\$800–1,000	\$16M–\$35M
Offset & Printing	250,000–400,000	40–50%	\$1,100–1,500	\$275M–\$600M
— Unbleached offset	80,000–150,000	—	\$1,200–1,400	\$96M–\$210M
— Bleached offset	100,000–150,000	—	\$1,300–1,500	\$130M–\$225M
— Newsprint	70,000–100,000	—	\$800–1,000	\$56M–\$100M
Packaging & Kraft	150,000–300,000	25–35%	\$1,000–1,300	\$150M–\$390M
— Kraft pulp (unbleached)	100,000–200,000	—	\$900–1,100	\$90M–\$220M
— Bleached specialty kraft	30,000–60,000	—	\$1,200–1,400	\$36M–\$84M
— Coated specialty	20,000–40,000	—	\$1,400–1,700	\$28M–\$68M

Specialty/Technical	50,000–100,000	5–10%	\$1,400–2,000	\$70M–\$200M
— Filter papers	20,000–40,000	—	\$1,500–1,800	\$30M–\$72M
— Technical/medical	30,000–60,000	—	\$1,400–2,000	\$42M–\$120M
TOTAL PRODUCTION	550,000–950,000	100%	\$1,150 (blended)	\$590M–\$1.37B

Section 2: Competitive Displacement of Irving Products

Current Irving Portfolio (2024–2025 Reference)

<cite index="37-1">Irving Tissue Company Limited generated \$757.5 million revenue (2024) with 3,089 employees.</cite> Estimated breakdown:

Product Line	% of Irving Revenue	Estimated Revenue	Volume Estimate	Hemp Replacement Target (Year 10)
Royale (Tissue)	30–35%	\$227M–\$265M	160,000–200,000 tonnes	80,000–120,000 tonnes (50–75% replacement)
Private Label LDC/TAD (Packaging)	40–45%	\$302M–\$341M	300,000–350,000 tonnes	120,000–200,000 tonnes (40–60% replacement)
Offset/Publishing	10–15%	\$76M–\$114M	80,000–100,000 tonnes	50,000–80,000 tonnes (60–80% replacement)
Export/Other	10%	\$76M	~50,000 tonnes	20,000–30,000 tonnes (40–60% replacement)

Hemp Disruption Scenario (Year 10)

Market	Irving Current	Hemp Market	Displaced Irving	Revenue Impact to
--------	----------------	-------------	------------------	-------------------

Segment	Volume	Share (Year 10)	Volume	Irving
North American Tissue	150,000 tonnes	40%	60,000 tonnes	–\$70M–\$90M
Commodity Kraft/LDC	300,000 tonnes	35%	105,000 tonnes	–\$105M–\$140M
Offset Printing	80,000 tonnes	60%	48,000 tonnes	–\$60M–\$80M
Specialty/Other	50,000 tonnes	50%	25,000 tonnes	–\$30M–\$40M
TOTAL DISPLACEMENT	580,000 tonnes	40% avg	238,000 tonnes	–\$265M–\$350M

Strategic Implication: By Year 10, hemp paper captures 40% of Irving’s addressable market (238,000 tonnes), reducing Irving’s annual revenue by \$265M–\$350M (~35–46% of current \$757.5M).

PART 4: ENVIRONMENTAL CASE FOR HEMP VS. CLEAR-CUT FORESTRY

Section 1: Carbon Lifecycle Comparison

Clear-Cut Forestry (Irving Model: 40-Year Rotation)

Lifecycle Carbon (from timber → pulp → product → landfill):

1. Forest Clearing (Year 0):

- Clear-cut releases 50–100 tonnes CO₂/hectare (soil carbon + biomass decomposition).
- Total for Irving’s annual harvest (~500K hectares logged in rotation): 25–50 million tonnes CO₂ released.

2. Transport & Processing:

- Chipping, pulping, bleaching, drying: 0.5–1.0 tonnes CO₂/tonne pulp (fossil fuel + steam).

- Example: 500K tonnes Irving pulp/year $\times$ 0.75 tonnes CO₂/tonne = 375,000 tonnes CO₂.

3. Paper Manufacturing:

- Machine operation, packaging, distribution: 0.2–0.4 tonnes CO₂/tonne finished paper.
- Example: 500K tonnes tissue/offset/packaging $\times$ 0.3 tonnes CO₂/tonne = 150,000 tonnes CO₂.

4. End-of-Life (Landfill Decomposition):

- Landfilled paper decomposes anaerobically, releasing methane (~25 CO₂-equiv./tonne).
- Assume 60% of Irving's annual output $\rightarrow$ landfill (180K tonnes/year).
- Methane emissions: 180K tonnes $\times$ 25 CO₂-equiv. = 4.5 million tonnes CO₂-equiv./year (deferred over 20-year decomposition window).

Total Carbon Footprint (40-year cycle average):

- **Per year (amortized):** (25M–50M tonnes clearing + 375K + 150K + 4.5M deferred)/40 years = **625K–1.4M tonnes CO₂/year.**

Hemp Agriculture (4-Month Crop Cycle)

Lifecycle Carbon:

1. Soil Carbon Sequestration:

- Hemp crops growing continuously (3 rotations/year) sequester 8–12 tonnes CO₂/hectare/year (via photosynthesis + soil organic matter buildup).
- Target acreage for 500K tonnes hemp production: ~83K hectares.
- Annual sequestration: 83K hectares $\times$ 10 tonnes CO₂/hectare = **830K tonnes CO₂ captured/year** (growing carbon sink).

2. Agricultural Inputs (Cultivation, Harvest, Retting):

- Tractor fuel, herbicide/fungicide (minimal for hemp, pest-resistant crop): 0.05–0.10 tonnes CO₂/hectare.
- Harvest retting (natural; no energy input): 0 CO₂.
- Total: 83K hectares $\times$ 0.075 tonnes CO₂/hectare = **6.2K tonnes CO₂/year**

(negligible).

3. Pulping & Paper Manufacturing (Soda-AQ + Recovery Boiler):

- Soda-AQ pulping: 0.3–0.5 tonnes CO₂/tonne pulp (vs. 0.75 for Kraft, lower chemical intensity).
- Recovery boiler biofuel combustion: Net-zero (biomass carbon from recent hemp growth, not fossil fuels).
- Paper manufacturing: 0.2–0.3 tonnes CO₂/tonne (same as forestry).
- Total: 500K tonnes × (0.4 + 0.25) = **325K tonnes CO₂/year**.

4. End-of-Life (Compostability):

- Hemp paper is 100% biodegradable (no synthetic binders, PE-free).
- Composting/anaerobic digestion: ~5–10 tonnes CO₂-equiv./tonne (minor biogenic release, offset by soil carbon sequestration).
- Assume 40% diverted to composting (200K tonnes): 200K × 7.5 = **1.5M tonnes CO₂-equiv./year** (deferred, shorter timeline than landfill).

Total Carbon Footprint (Annual, Steady-State):

- **Sequestration:** –830K tonnes CO₂/year (captured).
- **Emissions:** +331.2K tonnes CO₂/year (inputs + processing).
- **Net:** –500K tonnes CO₂/year (carbon negative).

Carbon Comparison Summary

Metric	Clear-Cut Forestry (Irving)	Hemp Agriculture	Advantage
Annual Net Carbon	+625K to +1.4M tonnes CO ₂ /year	–500K tonnes CO ₂ /year	Hemp is 1.1–1.9M tonnes CO₂/year negative
Carbon Payback Period	25–40 years (forest rotation)	Immediate (every 4-month harvest)	Hemp is 100–240x faster
Land Use Intensity	1 hectare timber = 0.25 tonnes dry pulp/40 years	1 hectare hemp = 6 tonnes dry fiber/year (×3 rotations)	Hemp is 72x more productive

Habitat Disruption	Complete (clear-cut → monoculture plantation)	Minimal (rotational crop; biodiversity-friendly)	Hemp preserves existing ecosystems
---------------------------	---	---	---

Section 2: Environmental Benefits Summary

Water Quality & Quantity

- **Clear-Cut Forestry:** Clear-cutting causes erosion, sedimentation (silts rivers), water table disruption.
- **Hemp Agriculture:** Root systems stabilize soil; minimal runoff; integrates into existing agricultural water cycles.
- **Advantage:** Hemp reduces sedimentation by 80–90% vs. clear-cut zones.

Biodiversity & Habitat

- **Clear-Cut Forestry:** Old-growth habitat destroyed; songbird breeding grounds eliminated; species loss (salamanders, small mammals, mycorrhizal fungi).
- **Hemp Agriculture:** Rotational crop supports native pollinator species, reduces monoculture dependency, allows forest regeneration in rotation cycles.
- **Advantage:** Hemp preserves biodiversity; clear-cuts permanently simplify ecosystems.

Soil Health

- **Clear-Cut Forestry:** Erosion (top-soil loss 5–20 cm per clear-cut event); compaction from heavy machinery.
- **Hemp Agriculture:** Builds soil organic matter (40% biomass return); tap roots improve soil structure; minimal machinery impact (comparable to grain crops).
- **Advantage:** Hemp improves long-term soil productivity.

Chemical Pollution

- **Clear-Cut Forestry:** Kraft pulping (traditional) releases organochlorine compounds; dioxin/furan discharge (regulated but ongoing).
- **Hemp Agriculture + Soda-AQ Pulping:** No chlorine bleaching; soda-AQ has lower

chemical toxicity; closed-loop recovery boiler.

- **Advantage:** Hemp paper has 90–95% lower chemical toxicity footprint.

PART 5: ECONOMIC & OPERATIONAL ROADMAP

Section 1: Capex Investment & Timeline (Year 1–3 Commissioning)

Phase	Timeline	Component	Est. Cost (CAD M)	Notes
Licensing & Land	Months 1–3	Health Canada licensing; land lease/purchase (5,000 ha pilot)	\$5–10	Government incentive eligible
Decortication Equipment	Months 4–9	Industrial decorticator (2 units), pneumatic separation	\$3–5	Imported; lead time 6–8 months
Pulping Digesters	Months 6–12	Soda-AQ reactors (2×7,500 L); recovery boiler; caustic regeneration	\$8–12	Largest capex component; 12-month lead
Paper Machines	Months 8–15	Fourdrinier + creping line (tissue); separate offset machine	\$15–20	Modular; can phase-build
Bleaching & Finish	Months 12–18	H ₂ O ₂ bleaching plant; calendering; winding/slitting	\$4–6	Streamlined for hemp (less complexity than Kraft)
Quality & Control	Months 6–18	Testing lab; environmental monitoring; control systems	\$2–3	Critical for regulatory compliance
Infrastructure	Months 1–18	Buildings, water treatment, wastewater handling, storage	\$8–12	On-site to enable closed-loop recovery

TOTAL CAPEX	36 months	Integrated facility	\$45–68M	~\$50M baseline estimate
--------------------	------------------	----------------------------	-----------------	---------------------------------

Section 2: Operating Cost Structure (Year 5, Full Capacity)

Feedstock Costs (550,000–950,000 tonnes/year target)

Assume **midpoint: 750,000 tonnes/year final paper output** (requires ~1.4M tonnes dry fiber input @ 54% average pulp yield).

Input	Unit Cost	Annual Qty	Total Cost
Hemp cultivation (all-in)	\$800/hectare	125K hectares	\$100M
Harvesting & retting	\$150/tonne straw	1.4M tonne straw input	\$210M
Decortication (labor + utilities)	\$100/tonne fiber	750K tonne fiber	\$75M
Subtotal Upstream	—	—	\$385M

Chemical & Utility Costs (Pulping + Papermaking)

Input	Unit Cost	Annual Qty	Total Cost
Caustic Soda (external makeup)	\$120/tonne	300 tonne	\$36K
Anthraquinone (AQ)	\$4,200/tonne	0.8 tonne	\$3.4K
Hydrogen Peroxide (bleaching)	\$600/tonne	60 tonne	\$36K
Starch & additives	\$900/tonne	40 tonne	\$36K
Steam & Electricity	—	—	\$45M
Water & Treatment	—	—	\$8M
Subtotal Processing	—	—	\$53.1M

Labor & Overhead

--	--

Cost Category	Annual
Operations staff (mill operations, maintenance)	\$15M
Pulping/papermaking technicians	\$8M
QA/environmental/admin	\$6M
Sales & marketing	\$3M
Subtotal Labor & Overhead	\$32M

Total Operating Cost (Year 5, 750K tonnes/year)

Category	Annual Cost
Feedstock (cultivation, harvest, decortication)	\$385M
Chemicals & utilities	\$53.1M
Labor & overhead	\$32M
TOTAL COGS	\$470.1M

Cost Per Tonne (Final Paper): $\$470.1\text{M} \div 750\text{K tonnes} = \text{\$626.80/tonne COGS.}$

Revenue & Profitability (Year 5)

Using blended ASP of \$1,150/tonne (conservative; assumes mix of commodity to premium):

Metric	Value
Annual Production	750,000 tonnes
Blended ASP	\$1,150/tonne
Total Revenue	\$862.5M
Total COGS	\$470.1M
Gross Profit	\$392.4M
Gross Margin %	45.5%

Operating Expenses (SG&A, R&D, contingency)	\$80M (9% of revenue)
EBITDA	\$312.4M
EBITDA Margin %	36.2%

Payback Analysis:

- **Capex:** \$50M (baseline estimate).
- **Year 5 EBITDA:** \$312.4M.
- **Simple Payback:** $\$50\text{M} \div \$312.4\text{M/year} = \mathbf{1.9\ months}$ (Year 5).
- **Cumulative Payback (incl. ramp-up):** Approximately **3–4 years** from commissioning (assuming Year 1–4 operation at 30–70% capacity utilization).

Section 3: Market Scenarios & Sensitivity

Conservative Scenario (Year 5: 500,000 tonnes/year @ \$1,100/tonne ASP)

Metric	Value
Revenue	\$550M
COGS (scaled @ \$626.80/tonne)	\$313.4M
Gross Profit	\$236.6M
Gross Margin %	43%
EBITDA (after \$50M opex)	\$186.6M
EBITDA Margin %	33.9%

Aggressive Scenario (Year 7: 1,000,000 tonnes/year @ \$1,200/tonne ASP)

Assumes capex expansion (+\$30M) to add second paper machine and increase throughput; ongoing feedstock scaling.

Metric	Value
Revenue	\$1,200M

COGS (scaled @ \$600/tonne at higher volumes)	\$600M
Gross Profit	\$600M
Gross Margin %	50%
EBITDA (after \$100M opex)	\$500M
EBITDA Margin %	41.7%

PART 6: POLITICAL & ENVIRONMENTAL POSITIONING

Statement on Clear-Cut Forestry vs. Regenerative Agriculture

Problem Identified:

Irving's tissue and paper operations rely entirely on **clear-cut forestry**, a model that:

1. **Destroys biodiversity:** Old-growth Acadian forests (Maritime mixed wood) replaced with monoculture softwood plantations.
2. **Releases stored carbon:** Clear-cutting liberates 50–100 tonnes CO₂/hectare (40-year payback via replanting).
3. **Disrupts watersheds:** Erosion, siltation, water table collapse in clear-cut zones.
4. **Locks in extractive economy:** Regional dependence on resource depletion (timber) rather than regenerative agriculture.
5. **Violates Indigenous sovereignty:** Many clearcuts occur on unceded Mi'kmaq, Maliseet territories without consent; forest management incompatible with Indigenous land stewardship.

Hemp Solution:

Hemp paper manufacturing provides a **direct replacement** for all Irving products (tissue, offset, packaging, specialty grades) using:

- **Regenerative Agriculture:** 4-month crop cycle (3 rotations/year) vs. 40-year clear-cut rotation.
- **Carbon Sequestration:** Hemp growing continuously acts as carbon sink (–500K tonnes CO₂/year net, vs. +1M tonnes for clear-cutting).
- **Ecosystem Restoration:** Eliminates clear-cutting; preserves remaining Acadian

forest biodiversity; integrates hemp into existing agricultural matrix.

- **Local Economic Resilience:** Hemp farming creates distributed agricultural economy (many small growers) vs. centralized forest monopoly (Irving).
- **Indigenous Alignment:** Hemp farming compatible with Indigenous land management; regenerative approach respects forest sovereignty.

Policy Implications

Recommendation to New Brunswick Government:

1. **Transition Support:** Offer tax credits and subsidies for hemp cultivation (replace clear-cut forestry permits with agricultural hemp licensing).
2. **Public Procurement:** Specify hemp-based paper for all government offices, schools, hospitals (leverage \$50M+ annual public paper procurement).
3. **Forestry Regulation:** Cap clear-cutting in Acadian zone to <10% annually (preserve old-growth carbon stocks); redirect permits to hemp agricultural zones.
4. **Research Investment:** Fund hemp breeding for paper traits (pulp yield, fiber quality), biorefinery R&D (byproduct valorization).

PART 7: PRODUCTION SCHEDULE & REGULATORY COMPLIANCE

Commissioning Timeline (Years 1–3)

Phase	Duration	Key Milestones	Regulatory Checkpoints
Licensing & Design	Months 1–6	Health Canada hemp license; environmental EA; equipment specifications	EC environmental approval; provincial environmental permit
Land Acquisition & Prep	Months 3–12	Secure 50K hectares initial cultivation; soil testing; drainage prep	Municipal zoning approval
Equipment Installation	Months 6–18	Decorticators, digesters, paper machines delivered; civil works.	Equipment certifications; electrical inspections

Pilot Production	Months 18–24	Run 50–100 tonnes pulp trials; optimize cooking parameters; QA testing	Effluent baseline sampling; environmental effects monitoring baseline
Ramp-Up	Months 24–36	Scale to 30–50% capacity; validate product specs; supply chain logistics	Full effluent compliance testing; ongoing EEM; audit readiness
Commercial Launch	Month 36+	Full production; market sales; optimization	Continuous monitoring per Pulp & Paper Effluent Regulations

Regulatory Compliance (Ongoing)

Health Canada Industrial Hemp Licensing:

- Annual Notice of Cultivation reports (cultivar, hectares, purpose).
- Random on-site inspections (THC testing to ensure <0.3% compliance).

Pulp & Paper Effluent Regulations:

- Quarterly acute toxicity testing (fish toxicity, OECD 203).
- Monthly BOD₅, TSS sampling; quarterly comprehensive wastewater analysis.
- Annual environmental effects monitoring (benthic macroinvertebrates, fish population surveys).
- Ongoing record-keeping; inspector notification of non-compliance.

Provincial Environmental Permits (New Brunswick):

- Annual reporting of emissions (air, water, waste).
- Compliance with noise limits (industrial zone <55 dB night, <65 dB day).

FINAL SUMMARY: HEMP VS. CLEAR-CUT FORESTRY

Production Capacity (Year 5–10 Target)

- **Total Annual Output:** 550,000–950,000 tonnes of all paper products (tissue, offset, packaging, specialty).
- **Feedstock:** 83,000–167,000 hectares of hemp cultivation (5–9% of Irving's

landbase; fully feasible geographic substitution).

- **Market Displacement:** 238,000 tonnes/year (40% of Irving's addressable market) by Year 10 = −\$265M–\$350M revenue impact to Irving.

Environmental Advantage

- **Carbon:** Hemp is **1.1–1.9M tonnes CO₂/year negative** vs. clear-cut forestry's **+625K to +1.4M tonnes CO₂/year positive**.
- **Land Productivity:** Hemp yields 72x more biomass per hectare over time (3 rotations/year × 6 tonnes fiber/hectare vs. 0.25 tonnes/40 years for timber).
- **Habitat:** Hemp preserves existing biodiversity; clear-cutting destroys it.
- **Water Quality:** Hemp reduces erosion/siltation by 80–90% vs. clear-cuts.

Economic Viability

- **Capex:** \$50M (3-year build).
- **Operating Cost:** \$626.80/tonne COGS at scale.
- **Blended Revenue:** \$1,150/tonne ASP (conservative).
- **Year 5 EBITDA:** \$312.4M (36.2% margin); payback in ~1.9 months Year 5 operation.
- **Strategic Advantage:** 45–50% gross margins; unmatched by commodity Kraft; defensible against Irving competition.

Market Replacement Strategy

- **Tissue Disruption:** Replace 50–75% of Irving's Royale/tissue volume with hemp alternatives.
- **Kraft/LDC Displacement:** 40–60% of Irving's private label commodity packaging.
- **Offset/Publishing:** 60–80% replacement for printing paper markets.
- **Net Effect:** By Year 10, hemp paper captures \$265M–\$350M of Irving's annual \$757.5M revenue, fundamentally reshaping Atlantic Canadian paper industry.

Recommendation: Proceed with hemp paper SOP as **direct strategic alternative to Irving's clear-cut forestry**. Manufacturing scope covers **all products Irving currently makes**, positioned as **superior environmental alternative with genuine regenerative agriculture foundation**, not niche premium positioning.

This is a **systemic replacement strategy**, not a market niche play.