

Resonant Two-Photon Synthesis of Carbon Nanothreads

Background: Carbon nanothreads (also known as diamond nanothreads) are one-dimensional, fully sp^3 -bonded carbon polymers with exceptional predicted strength and stiffness ¹. In 2015, Badding *et al.* demonstrated the first benzene-derived nanothreads by compressing liquid benzene at extreme pressures (~20–30 GPa) ¹. The resulting material consists of densely packed, sub-nanometer carbon threads (diameter ~6.5 Å) whose mechanical properties “may exceed that of sp^2 nanotubes or high-strength polymers” ¹. However, such high pressures pose a scale-up barrier. Importantly, furan (C_4H_4O) is a less-aromatic aromatic: its [4+2] cycloaddition barrier (≈ 35 kcal/mol) is much lower than benzene’s (>46 kcal/mol) ². Indeed, slow compression of furan in a diamond anvil cell produced crystalline nanothreads at only 10–15 GPa ³ – the lowest reaction pressure reported to date ⁴. These furan-derived threads feature oxygen-containing ether linkages in every repeat unit ⁴, which can **improve composite integration** (e.g. by facilitating intercalation or bonding to polymers) ⁵.

Renewable Precursors: Crucially, furan can be sourced from biomass (e.g. agricultural waste) via furfural. Furfural is produced by hydrolyzing and dehydrating hemicellulose (xylan) from lignocellulosic feedstocks ⁶. In practice, cellulose and hemicellulose from industrial hemp, corn stover, sugarcane bagasse, etc., can yield furan (often through a furfural intermediate) in high purity using green processes (supercritical CO_2 extraction, acid-free hydrolysis, etc.). This enables a **carbon-negative, solvent-free supply chain** for furan, aligning with sustainability goals ⁶. Thus, the proposed route uses 100% bio-derived, non-GMO precursors and avoids toxic catalysts or solvents.

Two-Photon Laser Initiation




Figure: Jablonski diagram of degenerate two-photon excitation. Two simultaneous photons (red arrows) are absorbed to reach an excited state from the ground state, a process that can enable volumetric polymerization deep inside a transparent medium ⁷.

Instead of thermally or UV-initiating the polymerization, we employ **resonant two-photon absorption (TPA)** using a 450 nm femtosecond laser. In TPA, two photons of sub-gap energy are absorbed simultaneously by the furan molecule, effectively summing to an excitation energy of ~ 5.5 eV (2×2.75 eV)⁷. In practice, this means using 450 nm (blue) pulses (100 fs duration, 1 kHz rep. rate) tightly focused through the transparent moissanite anvil onto the furan sample. By choosing the photon energy to match half the $S_0 \rightarrow S_1$ transition of the pressurized furan crystal, the two-photon process **resonantly excites** the molecules, triggering the [4+2] cycloadditions that form nanothreads.

Two-photon initiation has critical advantages over one-photon UV: it is inherently *three-dimensional*. Because the absorption probability is highest only at the focal point (where photon density is greatest), the laser can **write polymerization deep into the sample volume**, not merely at the surface. This 3D “volumetric” polymerization is the same principle exploited in two-photon 3D lithography⁸. In our case, it means the entire $\sim$ mm-scale furan core can be converted uniformly. In situ Raman monitoring is used to track progress: the loss of the ~ 1600 cm^{-1} sp^2 ring stretch and growth of the ~ 1330 cm^{-1} sp^3 (diamondoid) peak indicate polymerization. Irradiation is stopped once the sp^3 Raman peak reaches $\sim 80\%$ intensity, yielding highly crystalline nanothreads. (This method mirrors published observations in furan DAC experiments, where fluorescence rises sharply and Raman ring modes disappear upon nanothread formation³.)

High-Pressure Apparatus and Procedure

To achieve ~ 5 GPa uniformly over a large volume, we replace the small (~ 0.1 mm^3) diamond anvils with *moissanite* (6H-SiC) anvils and plan to use large-volume piston-cylinder presses. Xu *et al.* (2000) demonstrated that moissanite anvils can reach >50 GPa and have optical properties rivaling diamond⁹. Crucially, moissanite cells allow **$\sim 1000\times$ larger sample volumes** than diamond anvils⁹, enabling gram-scale yields. In practice, a tungsten carbide piston-cylinder outfitted with sapphire or moissanite optical windows will compress the furan to ~ 5 GPa. Laser pulses are delivered via an optical fiber through the window, focused onto the sample. Raman spectra are recorded in situ to verify polymerization.

Standard Operating Steps:

- **Cell Loading:** Prepare two ~ 5 mm diameter moissanite anvils with cleaned surfaces. A 50 μm Re gasket is pre-indented and drilled. Load 99.9% pure furan (bio-derived) into the gasket hole under N_2 to avoid contaminants.
- **Pressure Ramp:** Close the cell and increase pressure slowly to ~ 5.0 GPa hydrostatically. Use ruby fluorescence or other calibrant to verify pressure stability.
- **Laser Irradiation:** Focus the 450 nm femtosecond laser through the moissanite window onto the furan. Fire pulses at ~ 1 kHz. The sample is transparent at 450 nm, so the beam penetrates into the interior.
- **Monitoring:** Continuously record Raman spectra (every ~ 30 s). Initially, prominent ~ 1600 cm^{-1} (sp^2) peaks dominate. As polymerization proceeds, a ~ 1330 cm^{-1} (sp^3 diamond) peak emerges and grows. Stop the laser when the sp^3 peak reaches $\sim 80\%$ of the original sp^2 intensity (indicating $\sim 80\%$ conversion).
- **Recovery:** Slowly decompress the cell back to ambient pressure. Retrieve the solid product, which should be a white/tan nanothread-rich material.

Throughout, no high-temperature heating is applied; all reaction energy comes from the laser. This avoids carbonization or loss of oxygen (a common problem in thermal compression). The ordered furan lattice at 5 GPa (Phase III) directs the [4+2] cycloaddition so that *unbranched, crystalline* nanothreads form, rather than amorphous carbon. (High-pressure spectroscopy studies show that furan already transitions to an ordered solid by ~ 4 – 5 GPa.)

Properties and Implications

The resultant **furan nanothreads** are expected to combine the diamond-like core strength of carbon nanothreads with built-in chemical functionality. Prior work shows furan nanothreads have >95% of carbons with single C-H bonds (sp^3) and only trace unsaturated/defect sites ¹⁰. They pack into hexagonal crystals of ~6.5 Å diameter threads ¹¹. Owing to the strong sp^3 network, these materials should exhibit *astounding stiffness*: predicted Young's modulus ~900 GPa (far above steel, approaching diamond) ¹ ¹². In practice, they promise a **weight-to-strength ratio** unmatched by conventional carbon fibers or CNTs ¹.

Moreover, the presence of periodic ether linkages ($-CH_2-O-CH_2-$) along the thread axis grants chemical reactivity and compatibility with polymer matrices. This built-in polarity can facilitate bonding to resins or metal intercalation, enabling truly high-performance **bio-composite frameworks**. Indeed, Huss *et al.* note that oxygen in each repeat unit will ease post-processing (e.g. metalation or exfoliation) for composite use ⁵.

Importantly, moving from diamond DACs to moissanite-based large-volume presses yields a **1000× scale-up** (from mm³ to cm³ samples) ⁹. This jump in sample volume (from milligrams to grams per run) is critical for industrial viability. Coupled with the 37% or greater reduction in required pressure (5 GPa vs. ~8–15 GPa in prior approaches), the process stress on equipment is greatly reduced. Two-photon laser initiation also means the reaction can occur at room temperature and without any catalyst, fulfilling a "cold synthesis" paradigm.

Advantages at a glance:

- *Exceptional materials*: Furan nanothreads combine diamond-like strength with tunable chemistry ¹ ⁵.
- *Renewable feedstock*: Uses bio-waste (hemp, corn, sugarcane) to produce furan via green chemistry ⁶.
- *Mild conditions*: Achieves polymerization at only ~5 GPa with laser assistance, greatly below previous thresholds ³.
- *Volumetric control*: Two-photon laser allows 3D polymerization throughout the bulk (not just surface) ⁸.
- *Scalable volumes*: Moissanite/LVP approach enables gram-scale yields (~1000× DAC) ⁹.
- *No toxic catalysts or residue*: Supercritical CO₂ extraction and acid-free methods ensure a clean product stream.

In summary, this resonant two-photon method unlocks a new regime of **cold, scalable nanothread synthesis**. It decouples polymerization from extreme mechanical shock by using precise photonic energy, while leveraging sustainable inputs. If successful, it could render traditional carbon fibers obsolete: one obtains ultra-strong, 1D carbon materials with inherent functionalization directly from plant waste. Such nanothreads, woven into the "Hempoxies" composite matrix, would enable the first truly **post-petroleum aerospace chassis**, marrying top-end performance to a green supply chain.

Sources: Key facts and methods are drawn from recent literature on furan nanothreads and high-pressure photochemistry ¹ ⁴ ² ⁶ ⁹ ⁷ ⁸, including the referenced preprint by Landry *et al.*. The two-photon polymerization principles are well-established in photonics and materials science ⁷ ⁸.

1 Benzene-derived carbon nanothreads - PubMed

<https://pubmed.ncbi.nlm.nih.gov/25242532/>

2 3 4 5 Microsoft Word - Elacqua - furan NTs - 2020.docx

<https://pdfs.semanticscholar.org/296d/ba4a63817efd2ecbdb831aac74623513b6df.pdf>

6 Furfural production from lignocellulosic biomass: one-step and two-step strategies and techno-economic evaluation - Green Chemistry (RSC Publishing)

<https://pubs.rsc.org/en/content/articlelanding/2024/gc/d4gc00883a>

7 File:Two Photon Excitation Diagram.png - Wikimedia Commons

https://commons.wikimedia.org/wiki/File:Two_Photon_Excitation_Diagram.png

8 Two-photon polymerization for 3D biomedical scaffolds: Overview and updates - PMC

<https://pmc.ncbi.nlm.nih.gov/articles/PMC9441635/>

9 Moissanite: a window for high-pressure experiments - PubMed

<https://pubmed.ncbi.nlm.nih.gov/11052937/>

10 Perfect and Defective ¹³C-Furan-Derived Nanothreads from Modest-Pressure Synthesis Analyzed by ¹³C NMR - PubMed

<https://pubmed.ncbi.nlm.nih.gov/34130458/>

11 12 Carbon nanothread - Wikipedia

https://en.wikipedia.org/wiki/Carbon_nanothread